



STP Accent

STP Accent is a heat-insulating vibration-damping self-adhesive material.

The material is grey, elastic, evenly foamed, small-meshed polyethylene with partly ruptured closed cell structure, the facing layer without dints and the mounting layer, covered with anti-adhesive paper.

Coefficient nomination	Specification		Testing method
Thickness, mm	10±1,5	6±1,5	GOST 25015-81
Sealer thickness, mm	0,3-0,4		GOST 25015-81
Anti-adhesive layer-to-mounting layer bond strength, N/cm, min	0,05-0,20		GOST 17317-88
Material-to-mounting surface bond strength, N/cm, min	3		TD 2244-050-48214265-2006
Layer-to-layer bond strength, N/cm, min, for a multilayer semi-product	2,5		GOST 17317-88
Facing layer-to-polyethylene foam bond strength, N/cm, min	1,5		GOST 17317-88

Transportation and Storage

The materials mustn't be exposed to moisture during handling. Packages mustn't be dropped or bent while handling. Material packages must be transported horizontally on a plane surface in any roofed types of transport in accordance with the haulage rules for this type of transport under the conditions eliminating mechanical damages, deformation and moisture penetration. Material packages must be transported horizontally, in piles not higher than 3 m.

It's not allowed to put any metal or analogous objects on the packs.

Materials must be stored in piles in roofed warehouses, horizontally, on a plane surface, not closer than 1m to heating appliances, under conditions eliminating moisture or oil penetration and exposure to sunlight.

Exploitation and installation requirements

Exploitation requirements

The material must be installed on clean dry metal surfaces, including complex surfaces with bend radius of minimum 100 mm. To clean the material of dirt, it is recommended to use water with neutral abstergents, not containing organic solvents and alkali. Upon dismantling, the material can't be reused.

Preparation for installation

In case the material is stored or transported at temperature, lower than 0°C, before installation it must be kept at temperature (20±5) °C for not less than 24 h. The mounting surface must be cleaned of dust and dirt, unoiled with technical solvents and kept until completely dry.

Installation

Antiadhesive paper must be peeled off. The edge of the detail must be pressed to the mounting surface step-by-step, avoiding air blisters formation. The material mustn't be installed on dirty, corroded metal surfaces.

True extract
Quality Control Department Specialist
LLC "Standartplast"